

## Regranulate

## **HDPE SOLLITEN**

For above mentioned supply, the following values have been measured.

## **Technical data**

Parameter	Value	Unit
Melt Flow Rate (190°C/5,00 kg)	1,50	g/10 min
Humidity	0,20	%
Bulk weight	580	kg/m³
Ash content	2	%
Density	0,96	g/cm³
Charpy notched	20	kJ/m²
Tensile modulus	950	MPa
Tensile strength	22	MPa

<sup>\*</sup>the measured values relate to a specific batch and other batches may have slight differences in individual parameters.

Use: Extrusion

Color: Black

Storage: The material should be stored dry, free of direct sunlight, up to a maximum temperature of 50 °C.

Packaging: BigBag or octabin on palett

**Safety information:** refers to the primary material, for the regranulate before the product is used, customers and other users should have their own independent opinion that the product is suitable for the intended use.



Hřivínův Újezd 212 | 763 07 Velký Ořechov IČ: 03401065 | DIČ: CZ03401065

Tel.: +420 576 013 873 | www.sollau-cz.com

