

## Regranulate PP SOLLAPOL

For above mentioned supply, the following values have been measured.

### Technical data

Parameter	Value	Unit
Melt Flow Rate (230°C/2,16 kg)	14,389	g/10 min
Density	0,904	g/cm <sup>3</sup>
Humidity	0,042	%
Bulk weight	489,8	kg/m <sup>3</sup>
Ash content	0,028	%
Notch toughness	4,857	kJ/m <sup>2</sup>
Modulus of elasticity	1739	MPa
Yield strenght	36,7	MPa
Relative elongation at yield point	10,5	%

\*the measured values relate to a specific batch and other batches may have slight differences in individual parameters.

**Use:** Injection moulding

**Color:** Natural

**Storage:** The material should be stored dry, free of direct sunlight, up to a maximum temperature of 50 °C.

**Packaging:** BigBag or octabin on palett

**Safety information:** refers to the primary material, for the regranulate before the product is used, customers and other users should have their own independent opinion that the product is suitable for the intended use.

**SOLLAU CZ s.r.o.**

Hřivínův Újezd 212 | 763 07 Velký Ořechov

IČ: 03401065 | DIČ: CZ03401065

Tel.: +420 576 013 873 | [www.sollau-cz.com](http://www.sollau-cz.com)

